

Product Description	EGO SB 11 is a softplastic putty.
Typical Uses	For single glazing in timber and metal windows and their combinations according to groups 1 to 3 of RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim.
Application	Apply EGO SB 11 only onto dry and clean profiles that are free from substances liable to impair adhesion. Timber frames (moissture max. 15 %) must be painted prior to the application. Apply EGO SB 11 in sufficient quantity and without bubbles.
Please observe	DIN 18361 (Glazing work) DIN 18545 (Sealing of glazing with sealants) DIN 18363 (Paintwork) Technical directives for window paints Instructions 3 + 18 by Bundesausschuß Farbe und Sachwertschutz as well as EGO glazing systems In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.
Density	Approx. 2 g/cm ³ DIN EN ISO 10563
Application Temperature	+ 5° c to + 30° C
Service Temperature	Approx. - 30° C to + 80° C
Consistency	Softplastic
Properties	Non-shrinking
Method of Application	Manually or with EGOFIX Compressed Air Gun
Secondary Treatment	Smooth carefully with a polished putty knife Over-paint all putty surfaces with a weatherproof paint at the earliest after skin formation, at the latest after 8 weeks.
Standard Colour	Grey
Packaging	5 kg bucket 10 kg bucket 25 kg bucket Special packaging upon request
Storage	Store in cool and dry conditions in closed original packaging.